

CLIENT: **The Onyx Collection, Inc.**
105 Broadway Street
Belvue, KS 66407

Test Report No: TJ8201	Date: July 28, 2021
-------------------------------	----------------------------

SAMPLE ID: Tiramisu Gloss Smooth 48" x 36" Mid Height Center Drain Shower base, manufactured stone shower pan.

SAMPLING DETAIL: Test samples were submitted to the laboratory directly by the client. No special sampling conditions or sample preparation were observed by QAI.

DATE OF RECEIPT: Samples were received at QAI on July 15, 2021.

TESTING PERIOD: July 28, 2021

AUTHORIZATION: Signed Proposal 21JG0708-02 signed by Francis Awerkamp on July 8, 2021.

TEST PROCEDURE: ASTM F462-79 (Reapproved 2007) Standard Consumer Safety Specification for Slip-Resistant Bathing Facilities.

TEST RESULTS: The samples **meet** the criteria of ASTM F462-79. Detailed test results are presented in the subsequent pages of this report.

Prepared By

Signed for and on behalf of
QAI Laboratories, Inc.



Jarred Johnson
Laboratory Test Technician

Lawrence Gibson
Project Reviewer

Water Temperature: 70°F
 Initial Reference Surface Reading: 1.5 Coefficient of Friction: 0.11
 Final Reference Surface Reading: 1.6 Coefficient of Friction: 0.12

Measurement Zone	1	2	3	4	5	6	7	8	9
Reading 1	1.00	1.30	3.20	1.30	2.50	3.00	4.50	1.50	2.80
Reading 2	1.40	1.30	3.20	1.30	2.40	3.00	4.20	1.50	2.70
Average	1.20	1.30	3.20	1.30	2.45	3.00	4.35	1.50	2.75
Coef/Fric	0.08	0.09	0.28	0.09	0.20	0.26	0.41	0.11	0.24

Least Coefficient of Friction: 0.08
 Measurement Zone(s): 1
 Does the 1-1/2 x 3" template always touch textured area? Yes

Minimum requirement for coefficient of friction is **0.04**

*** END OF TEST REPORT ***